測試報告/ Test Report

億高應用材料股份有限公司 / Zirco Applied Materials Co., Ltd.

桃園市中壢區中大路300號中央大學育成中心233室 / 3F, No.71-1, Huanbei Rd., Zhongli Dist.,

Taoyuan City 32055, Taiwan

工服編號/ Application No. 20-04-WAH-050

承辦日期/ Date of Receipt 2020/4/20 測試日期/ Date of Performance 2020/4/21 報告日期/ Date of Issue 2020/5/11

委託機構/ Applicant 億高應用材料股份有限公司 / Zirco Applied Materials Co., Ltd.

桃園市中壢區中大路300號中央大學育成中心233室 / 3F, No.71-1, Huanbei Rd.,

Zhongli Dist., Taoyuan City 32055, Taiwan

聯絡人/ Contact

聯絡電話/ Tel 03-4204252

檢體名稱/ Sample Description Uplus NANO-AG Antibacterial Film

檢體資訊/ Sample Information 樣品批號/ Sample Lot Number: Uplus UATF-100AG

樣品製造日期/ Manufacture Date: —

樣品有效日期/ Expiry Date: —

樣品狀態/ Sample State: 散裝-室溫 / Packaging in bulk-Room temperature

樣品重量/ Sample Weight: 9片 / 9 pieces

製造廠商/國內負責廠商 Manufacturer/ Vender: 億高應用材料股份有限公司 Zirco Applied Materials Co., Ltd./ 億高應用材料股份有限公司 Zirco Applied

Materials Co., Ltd.

其他/ Others: -

備註/ Note:

- 1. 送测樣品及其相關訊息均由客戶提供並已經由客戶確認無誤,標 "—"者,係指客戶未提供該項資訊。/ Any sample and sample information listed in this test report are provided and identified by clients, except the labeled "—", (which is) meant the client offered no information about it.
- 2. 本報告僅對測試樣品負責。/ Unless otherwise stated the results shown in this test report refer only to the samples(s) tested.
- 3. 非經本中心同意,本報告內容不得以任何方式摘錄複印使用。/ This report cannot be reproduced without prior written permission of the laboratory.
- 4. 本報告缺頁無效。/ This report becomes void if all pages not included.
- 5. 测試項目有標★者,係指該項目經衛生福利部認證,且依認證之檢驗方法執行檢驗。/ The inspection items accrediated by MOHW are marked with "★", and inspected by the accrediated method.
- 6. 测试項目有標☆者,係指該項目經全國認證基金會認證,且依認證之檢驗方法執行檢驗。/ The inspection items accrediated by TAF are marked with "☆", and inspected by the accrediated method.
- 7. 本報告所載事項僅作為參考資料,不得作為商業廣告宣傳及訴訟之用。/ This report is for reference only and cannot be for any commercial purposes or litigation.
- 8. 测試項目若為定量分析以「定量極限」表示;以定性分析則以「偵測極限」表示。/ The inspection items are expressed as quantitative limits for quantitative analysis and as detection limits for qualitative analysis.
- 9. 测定值低於定量極限/偵測極限,以「未檢出」或「陰性」表示之。/ This testing result will be "N.D." or Negative for Limit of Detection, respectively.

報告簽署人/ Approved by:



連線線 車線線管 車輪岩電 電影電電

Laboratory Representative

檢驗報告僅就委託者之委託事項提供檢驗結果,不對產品合法性做判斷。
This report is the test results issued by the inspection institution are requested by the consignor and it is no relationship with the legitimacy of the product.

測試結果/ Test Results

測試項目	測試方法	測試結果		定量/偵測極限
Test Item(s)	Method	Test Results		LOQ/LOD
	依據JIS Z 2801:2010 (amd 1:2012) According to JIS Z 2801:2010 (amd 1:2012)	>99.99	%	

^{*}測試內容,詳如附件/ Please refer to the attached list for Test content

33383 桃園市龜山區文明路29巷8號 • 03-328-0026 • www.etc.org.tw



檢體照片/ Sample Photo



---報告結尾/ End of Report ---

33383 桃園市龜山區文明路29巷8號 · 03-328-0026 · www.**唐中下**木相符 No. 8, Lane 29, Wenming Rd., Guishan Dist. Taoyuan City 33383, Taiwan, R.O.C. 6-328-0026 · www.etc.org.tw

Page 3 of 3

附表 Attached list

測試內容 Test content: 抗菌試驗 Test for antimicrobial activity and efficacy

測試結果 Test results:

Res	ult		
試驗菌種 (保存編號) Bacterial strain to be used for the tests (Strain number)	Escherichia coli (BCRC 11634)		
起始菌量 Value of antimicrobial activity (A) (CFU/mL)	9.00 × 10 ⁵		
空白對照樣品菌量 Average of the number of viable cells of bacteria immediately after inoculation on the untreated test piece(U0)	1.37 × 10 ⁴ Log : 4.14		
作用時間 Incubation time	24hr		
空白對照樣品培養24hr後菌量 Average of the number of viable cells of bacteria on the untreated test piece after 24hr(Ut)	3.20. × 10 ⁶ Log : 6.51		
加工樣品培養24hr後菌量 Average of the number of viable cells of bacteria on the antimicrobial test piece after 24hr(At)	<0.63 Log: <0.63		
抗菌活性值 Antibacterial activity:R = Ut - At	>5.88		
抗菌效力 Antimicrobial efficacy(%)	>99.99		

備註 Remarks: CFU = 菌落形成單位 Colony Forming Unit

<= 小於 less than

>= 大於 greater than

抗菌效力 Antimicrobial efficacy(%) = (Ut-At)/Ut x 100%

Food Safety and Cosmeceutical Analysis Laboratory

工服編號/ Application No.: 20-04-WAH-050

附表 Attached list

Test Photo:



24hr Inoculum on untreated sample: Ut

24hr Inoculum on antibacterial treated sample: At



